


Tylose[®] MB 3003 P4

Technical Data Sheet



Product properties			
Constitution:	Methylhydroxyethyl cellulose modified		
Appearance:	powder	Delayed solubility:	no
Etherification:	high etherification	Thickening effect:	extreme
Particle size:	fine powder	Level of viscosity: according to Höppler	3000 mPa·s


Product specification	
Moisture:	≤ 6 %
Content of NaCl:	≤ 1.5 %
Particle size:	< 125 µm: min. 80 %
Particle size:	< 100 µm: min. 65 %
Viscosity:	4000 - 7000 mPa·s
Brookfield RV, 20rpm, 1.9%, 20°C, 20° GH	

Recommended fields of application
Tile adhesives, sag resistant
EIFS adhesives

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.

Tylose[®] MB 3003 P4

Technical Data Sheet



Application performance

Consistency development:	moderate	Water retention:	low
Final consistency:	very high	Influence on cement hydration:	high
Sag resistance:	very high	Heat stability:	low
Water demand:	high		

Packaging, Storage, Safety instructions

Like all fine-particle organic substances, cellulose ethers constitute a dust explosion hazard. Dust formation and deposits must be kept to a minimum so that no ignitable dust/air mixtures can form. Ignition sources such as naked flames, hot surfaces, sparks and static electricity should be avoided. Tylose starts to decompose at about 200°C. Its ignition temperature is >360°C. Tylose burns easily and the fire may spread.

When stored in closed containers, or in its original packaging in a dry place at room temperature, Tylose can be kept for a long time. In the case of high viscosity grades, a slow loss of viscosity can be measured after lengthy storage (>1 year). Tylose absorbs water from moist air. Once opened, container must be resealed and kept tightly closed.

This Tylose-type is supplied in multi-ply paper bags with polyethylene intermediate layer and/or in big bags.

This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described or their suitability for a particular application. Any existing industrial property rights must be observed. The quality of our products is guaranteed under our General Conditions of Sale.